


Inspection Certification	LKT-1276		
Customer	Skywalk	Stand	Rev. 1.2 - 28.06.2013
Testlocation	Bad Grönenbach	12,5 N	Messungenauigkeit
Date	10.04.16		
Bending	5000	Temp./humi.	20,1° - 44%
Line-Manufacturer	Edelrid		
Articel	8000-U-190	Line diameter	1,1 mm
Req. strength	1900 N		
Material	Aramid	Color	natur
length of seam - mm	70in50	Kind of seam	NZZ
Description/Norm	Bending test confirm EN 926-1 & LTF 91/09		

Results			
	Max. strength unbended	1768,0 N	93,1 % from req. Strength
	Max. strength Test 1	1343,0 N	70,7 %
	Max. strength Test 2	1281,0 N	67,4 %
	Max. strength Test 3	1230,0 N	64,7 %
	Test Result average	1284,7 N	Result with MU
	Test Result minimum	1230,0 N	1217,5 N



Bad Grönenbach, den 11.04.2016

Guido Feuerhahn

Inspector

EAPR GmbH

Test laboratory for Parachute- and Paraglidersystems