



Inspection Certification	LKT-1277		
Customer	Skywalk	Stand	Rev. 1.2 - 28.06.2013
Testlocation	Bad Grönenbach	12,5 N	Messungenauigkeit
Date	11.04.16		
Bending	5000	Temp./humi.	20,1° - 44%
Line-Manufacturer	Edelrid		
Articel	8000-U-230	Line diameter	1,4 mm
Req. strength	2300 N		
Material	Aramid	Color	nature
length of seam - mm	70in50	Kind of seam	NZZ
Description/Norm	Bending test confirm EN 926-1 & LTF 91/09		

Results			
	Max. strength unbended	1825,0 N	79,3 % from req. Strength
	Max. strength Test 1	1561,0 N	67,9 %
	Max. strength Test 2	1481,0 N	64,4 %
	Max. strength Test 3	1503,0 N	65,3 %
	Test Result average	1622,0 N	Result with MU
	Test Result minimum	1481,0 N	1468,5 N



Bad Grönenbach, den 11.04.2016


 Guido Heusch
 Inspector