


Inspection Certification	LKT - 950		
Customer	Skywalk	Stand	Rev. 1.4 - 05.09.2014
Testlocation	Bad Grönenbach	12,5 N	Messungenauigkeit
Date	10.03.15	MPM	006, 018, 019, 026, 038
Bending	5000	AA	
Line-Manufacturer	Edelrid	Temp./humi.	18,5° - 65%
Articel	8000U-050	Line diameter	0,5 mm
Req. strength	500 N		
Material	Aramid	Color	nature
length of seam - mm	70in35	Kind of seam	Step
Description/Norm	Bending test confirm EN 926-1 & LTF 91/09		

Results			
Max. strength unbended	564,0 N	112,8 % from req. Strength	
Max. strength Test 1	239,0 N	47,8 %	
Max. strength Test 2	291,0 N	58,2 %	
Max. strength Test 3	251,0 N	50,2 %	
Test Result average	260,3 N	Result with MU	
Test Result minimum	239,0 N	226,5 N	



Bad Grönenbach, den 10.03.2015

Guido Reuch

Inspector

EAPR GmbH

Test laboratory for Parachute- and Paraglidersystems