


Inspection Certification	LKT-951		
Customer	Skywalk	Stand	Rev. 1.2 - 28.06.2013
Testlocation	Bad Grönenbach	12,5 N	Messungenauigkeit
Date	10.03.15		
Bending	5000	Temp./humi.	15° - 70%
Line-Manufacturer	Edelrid		
Articel	8000U-90	Line diameter	0,8 mm
Req. strength	900 N		
Material	Aramid	Color	nature
length of seam - mm	70in35	Kind of seam	Stepstich-gespleißt
Description/Norm	Bending test confirm EN 926-1 & LTF 91/09		

Results			
Max. strength unbended	906,0 N	100,7 % from req. Strength	
Max. strength Test 1	591,0 N	65,7 %	
Max. strength Test 2	559,0 N	62,1 %	
Max. strength Test 3	615,0 N	68,3 %	
Test Result average	588,3 N	Result with MU	
Test Result minimum	559,0 N	546,5 N	



Bad Grönenbach, den 10.03.2015

Dennis Wiest

D. Wiest

Inspector

EAPR GmbH

Test laboratory for Parachute- and Paraglidersystems