


Inspection Certification			
Customer	Skywalk	Stand	Rev. 1.2 - 28.06.2013
Testlocation	Bad Grönenbach	12,5 N	Messungenauigkeit
Date	19.10.16		
Bending	5000	Temp./humi.	20,1° - 44%
Line-Manufacturer	Liros		
Articel	DC35	Line diameter	
Req. strength	350 N		
Material	Dyneema	Color	rose
length of seam - mm		Kind of seam	NZZ
Description/Norm	Bending test confirm EN 926-1 & LTF 91/09		

Results			
Max. strength unbended		341,0 N	97,4 % from req. Strength
Max. strength Test 1		388,0 N	110,9 %
Max. strength Test 2		404,0 N	115,4 %
Max. strength Test 3		373,0 N	106,6 %
Test Result average		388,3 N	Result with MU
Test Result minimum		373,0 N	360,5 N



Bad Grönenbach, den 20.10.2016

Guido R. ...
Inspector