


Inspection Certification	LKT-1611		
Customer	Skywalk	Stand	Rev. 1.2 - 28.06.2013
Testlocation	Bad Grönenbach	12,5 N	Messungenauigkeit
Date	04.04.17		
Bending	5000	Temp./humi.	20,1° - 44%
Line-Manufacturer	Edelrid		
Articel	8000U-70	Line diameter	
Req. strength	700 N		
Material	Aramid	Color	nature
length of seam - mm		Kind of seam	Step
Description/Norm	Bending test confirm EN 926-1 & LTF 91/09		

Results			
	Max. strength unbended	549,0 N	78,4 % from req. Strength
	Max. strength Test 1	312,0 N	44,6 %
	Max. strength Test 2	366,0 N	52,3 %
	Max. strength Test 3	323,0 N	46,1 %
	Test Result average	333,7 N	Result with MU
	Test Result minimum	312,0 N	299,5 N



Bad Grönenbach, den 04.04.2017


 Guido Heuser
 Inspector