


Inspection Certification	LKT-1610		
Customer	Skywalk	Stand	Rev. 1.2 - 28.06.2013
Testlocation	Bad Grönenbach	12,5 N	Messungenauigkeit
Date	04.04.17		
Bending	5000	Temp./humi.	20,1° - 44%
Line-Manufacturer	Edelrid		
Articel	8000U-130	Line diameter	
Req. strength	1300 N		
Material	Aramid	Color	nature
length of seam - mm		Kind of seam	NZZ
Description/Norm	Bending test confirm EN 926-1 & LTF 91/09		

Results		
Max. strength unbended	892,0 N	68,6 % from req. Strength
Max. strength Test 1	728,0 N	56,0 %
Max. strength Test 2	720,0 N	55,4 %
Max. strength Test 3	760,0 N	58,5 %
Test Result average	736,0 N	Result with MU
Test Result minimum	720,0 N	707,5 N



Bad Grönenbach, den 04.04.2017

Guido Reisch

Inspector