


Inspection Certification Rev. 1.0 -05.07.2017	1733		
Testlocation	Bad Grönenbach	Sensor/HZ	ME-KM26z-5 kN
Standard	926-1:2016 - 4.6	Amplifier/HZ	ME-GSV-2AS - 100 Hz
Date	31.07.2017	Last Calibration	D-L-17552-01-00- 2017-02
Inspector	Guido Reusch	Measuring uncertainty	12,5 N
Line-Manufacturer	Edelrid	Temp./humi.	22,7° - 63%
Articel	8000-90	Line diameter	0,8 mm
Req. Strength by Mf	900 N	Line length overall	500 mm
Material	Technora/-	Color	red
length of seam - mm	in60 / 45	Kind of seam	Step
Production description	23.06.2017, Rev. 1		

Results		
Max. strength unbended	940,0 N	104,4 % from req. Strength
Max. strength Test 1	712,0 N	79,1 %
Max. strength Test 2	603,0 N	67,0 %
Max. strength Test 3	550,0 N	61,1 %
Test Result average	621,7 N	Result with MU
Test Result minimum	550,0 N	537,5 N



Bad Grönenbach, 03.08.2017

Guido Reusch
Inspector

Needle
Thread

70
American Effierd Polyester Tex 45 bond threads

