

DESCRIPTION OF THE CHARACTERISTICS

1) FABRIC OF CANOPY

STÜCKLISTE

FABRIC CODE	FX47	
SUPPLIER NAME	TORAY INDUSTRIAL INC	
ADDRESS	NAKANOSHINA 3-CHOME, KITA-KU 530 JAPAN	
MATERIAL	POLYESTER	
WEIGHT (GR/SQ.M)	45 - 48	
BREAKING STRENGTH (KG/5CM)	WARP	46
	WEFT	37
TEAR STRENGTH (KG/5CM)	WARP	3.2
	WEFT	3.5
WEAVE DESIGN	RIPSTOP	
AIR POROSITY	0-0.01 (CC/SEC/C ²)	

2) SUSPENSION LINE

MATERIAL	ARMIDE YARN WITH NYLON SLEEVE	
SUPPLIER NAME	ARAMIDE MATSCHAPPIJ VOF (AKJO)	
ADDRESS	VELPERWEG 76, P.O. BOX 9300, 6800 SB, ARNHEM, NETHERLANDS	
DIAMETER (MM)	1.6	
YARN COUNT	1260 DTEX	
NUMBER OF ENDS	4	
BREAKING STRENGTH	130KG	

3) FABRIC OF FLARE

FABRIC CODE	T-64500	
SUPPLIER NAME	TEIJIN LIMITED	
ADDRESS	6-7, MINAMIHONMACHI, 1-CHOME, CHOU, OSAKA, JAPAN	
MATERIAL	POLYESTER WITH FILM LAMINATION	
WEIGHT (GR/SQ.M)	176	
BREAKING STRENGTH (KG/5CM)	WARP	137
	WEFT	118
TEAR STRENGTH (KG/5CM)	WARP	4.2
	WEFT	4.1
WEAVE DESIGN	PLAIN	

APOLLO-SPEED 27

finsterwalder GmbH
 HANNOVER 10000118 • D-3000 MÜNCHEN 10 • 0 89 311622

4) REINFORCEMENT TAPE

FABRIC CODE		T-64500
SUPPLIER	NAME	TEIJIN LIMITED
	ADDRESS	6-7, MINAMIHONMACHI, 1-CHOME, CHOU, OSAKA, JAPAN
MATERIAL		POLYESTER WITH FILM LAMINATION
WEIGHT (GR/SQ.M)		176
BREAKING STRENGTH (KG/5CM)	WARP	137
	WEFT	118
TEAR STRENGTH (KG/5CM)	WARP	4.2
	WEFT	4.1
WEAVE DESIGN		PLAIN

5) RISER

MATERIAL		POLYAMIDE 66 YARN
SUPPLIER	NAME	MONSANTO COMPANY
	ADDRESS	320 INTERSTATE, SUITE 500N, PARKWAY, ATLANTA, GA, 30339, USA
WEIGHT (GR/SQ.M)		22
BREAKING STRENGTH		850Kg
WIDTH (MM)		25

6) HARDWARE (CARABINER OF RISER)

MATERIAL	STEEL
BREAKING STRENGTH	5
DIAMETER (MM)	1300Kg