

DESCRIPTIVE OF THE CHARACTERISTICS

1)FABRIC OF CANOPY

FABRIC CODE		FX40		
SUPPLIER	NAME	TORAY INDUSTRIAL INC		
	ADDRESS	NAKANOSHINA 3-CHOME,KITA-KU 530 JAPAN		
MATERIAL		POLYESTER		
WEIGHT(GR/SQ.M)		38		
BREAKING STRENGTH (KG/5CM)	WARP	40		
	WEFT	30		
TEAR STRENGTH (KG/5CM)	WARP	SINGLE	2.2	
	WEFT	TONG-UE	2.4	
WEAVE DESIGN		RIPSTOP		
AIR POROSITY		0-0.01(CC/SQCM/SEC)		

2)SUSPENSION LINE

MATERIAL		ARMIDE YARN WITH NYLON SLEEVE		
SUPPLIER	NAME	ARAMIDE MATSCHAPPIJ VOF(AKJO)		
	ADDRESS			
DIAMETER(MM)		1.4		
VARN COUNT		1260 DTEX		
NUMBER OF ENDS		4		
BREAKING STRENGTH		130Kg		


finsterwalder GmbH

FINSTERWALDER GMBH • 34109 Kassel • Tel. (0561) 8115523

3) REINFORCING TYPE

FABRIC CODE	SCRIM W4.20	
SUPPLIER	NAME	PORCHER MARINE
	ADDRESS	: ROOM 803 SHU LAM BUILDING 23 LUARD ROAD , WANHAI , HONG KONG
WEIGHT(GR/SQ.M)		180
TEAR STRENGTH (DAN/5CM)	WARP	20
	WEFT	20

4) RISER

MATERIAL	POLYAMIDE 66 YARN	
SUPPLIER	NAME	MONSANTO COMPANY
	ADDRESS	320 INTERSTATE,SUITE 500N,PARKWAY,ATLANTA,GA,30339,USA
WEIGHT(GR/SQ.M)		22
BREAKING STRENGTH		850Kg
WIDTH(MM)		25

5) HARDWARE (CARABINER OF RISER)

MATERIAL	STAINLESS STEEL
BREAKING STRENGTH	1300Kg
DIAMETER(MM)	5