

DESCRIPTION OF MATERIALS

1. FABRIC OF CANOPY

FIBRIC CODE		PG3000KWR,PG3347K	
SUPPLIER	NAME	TORAY INDUSTRIES. INC	
	ADDRESS	TORAY BUILDING, 2-1, NIHONBASHI-MUROMACHI 2-CHOME, CHUO-KU TOKYOU 103-8666	
WEIGHT(g/M2)		42±1.5	
BREAKING STRENGHT (kg/5cm)	WARP	42±4	
	WEFT	36±4	
TEAR STRENGHT (kg)	WARP	3.0 MIN.	
	WEFT	3.0 MIN.	
WEAVE DESIGN		RIP STOP	
AIR POROSITY(cc/cm2/sec)		LESS THAN 0.03	

2. SUSPENSION LINE

MATERIAL		ARAMID(TECHNORA)			
SUPPLIER	NAME	MARUBENI COPORATION			
	ADDRESS	5-7 HOMMACHI 2-CHOME, CHUO-KU, OSAKA,541-8588,JAPAN			
DIAMETER(mm)		1.2	1.5	1.8	
YARN COUNT		1,000D	1,000D	1,000D	
NUMBER OF CORE		4	6	9	
BREAKING STRENGTH		80kg	120kg	180kg	

3. REINFORCEMENT

FIBRIC CODE		W420 SCRIM			
SUPPLIER	NAME	NCV INDUSTRIES			
	ADDRESS	75 RUE RUISSEAU ZI DE THARABIE BP 710 38297 ST QUENTIN FALLAVIER CEDEX FRANCE			
MATERIAL		POLYERSTER SCRIM			
WEIGHT(g/M2)		180			
BREAKING STRENGHT (kg/5cm)	WARP	137			
	WEFT	118			
TEAR STRENGHT (kg)	WARP	4.2			
	WEFT	4.1			
WEAVE DESIGN		RIP STOP			

4. RISER

